

# NERO IMPALA®



Country of origin		South Africa
Petrographic Composition		Plagioclase (64%), orthopyroxene (30%), clinopyroxene (4%), Amphibole (<1%), chlorite (<1%), sericite (<1%), talc (<1%)
Texture		Granular
Compressive strength	Mpa	240
Flexural strength	Mpa	22
Bulk specific gravity	Kg per m <sup>3</sup>	2,930
Porosity	% per mm	0,34
Water absorption	%	0,10

The information contained in the technical data sheet is obtained and provided by a third party. We have no control over said third party, and we therefore do not accept any responsibility or liability in any form whatsoever for the information contained therein.

No warranties, promises and/or representations of any kind, expressed or implied, are given as to the nature, standard, accuracy, content, completeness, legality, reliability or otherwise of the information provided in the technical data sheets nor to the suitability or otherwise of the information to your circumstances.

Under no circumstances will our company (including their owners, directors, partners, employees, agents, contractors, affiliates, successors-in-title and assigns) be liable for any loss or damage of any nature (including direct, indirect and consequential damages) arising from or in connection (directly or indirectly) with the use of the information contained in the technical data sheets provided. This limitation of liability will apply at all times and under all circumstances.